



KT Refractories US Company

Warehouse Address: 4583 S. Wayside Dr., Houston, TX 77087

Phone: 1877-365-2995 Fax: 713-838-2248

www.KTRrefractories.com

MgO-Al₂O₃ Spinel Bricks Technical Specs

MgO Al ₂ O ₃ Spinel Bricks	
PROPERTY	VALUE
Refractoriness	40 SK
Apparent Porosity	18.00%
Bulk Density	2.90 g/cm ³
Cold Crushing Strength	45 Mpa
Thermal Expansion at 1000°C	1.10%
Refractoriness under Load, (0.2MPa)T 2	1700°C
Thermal Conductivity at 1000°C	3.98 W/m · K
Spalling Resistance 1000°C~air cycle	20 cycles-0%
Chemical Analysis	
Al ₂ O ₃	≥12%
MgO	≥81%
Fe ₂ O ₃	≤1%
CaO	≤1.2%
SiO ₂	≤1%